

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 825 271 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
05.06.2002 Bulletin 2002/23

(51) Int Cl.7: **C23C 4/04, C23C 28/00**

(21) Application number: **97305581.7**

(22) Date of filing: **24.07.1997**

(54) **A metallic article having a thermal barrier coating and a method of application thereof**

Metallischer Artikel mit einer Wärmeschutzbeschichtung und Verfahren zum Aufbringen derselben

Article métallique ayant un revêtement faisant barrière thermique et méthode pour sa fabrication

(84) Designated Contracting States:
DE FR GB

(30) Priority: **16.08.1996 GB 9617267**

(43) Date of publication of application:
25.02.1998 Bulletin 1998/09

(73) Proprietor: **ROLLS-ROYCE plc**
London, SW1E 6AT (GB)

(72) Inventors:

- **Rickerby, David Stafford**
Duffield, Derbyshire DE26 4DS (GB)
- **Morrel, Paul**
Swadlincote, Derbyshire DE11 7ET (GB)
- **Tamarin, Yuriy Aleksandrovich**
Moscow 111555 (RU)

(56) References cited:

EP-A- 0 166 097	EP-A- 0 266 299
WO-A-94/08069	DE-A- 2 640 829
GB-A- 2 222 179	

EP 0 825 271 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a thermal barrier coating applied to the surface of a superalloy article e.g. a gas turbine engine turbine blade, and to a method of applying the thermal barrier coating. The invention particularly relates to ceramic thermal barrier coatings more particularly to stabilised zirconia thermal barrier coatings.

[0002] The constant demand for increased operating temperature in gas turbine engines was initially met by air cooling of the turbine blades and the development of superalloys from which to manufacture the turbine blades and turbine vanes, both of which extended their service lives. Further temperature increases necessitated the development of ceramic coating materials with which to insulate the turbine blades and turbine vanes from the heat contained in the gases discharged from the combustion chambers, again the operating lives of the turbine blades and turbine vanes was extended.

[0003] It is known in the prior art to apply these ceramic coating materials by the thermal, or plasma, spray process onto a suitable bond coating, for example a MCrAlY alloy bond coating, which has been applied to the metallic substrate.

[0004] It is also known in the prior art to apply these ceramic coating materials by the physical vapour deposition process onto a suitable bond coating which has an alumina interface layer, for example a MCrAlY alloy bond coating, which has been applied to the metallic substrate.

[0005] It is also known in the prior art to apply these ceramic coating materials by plasma spraying or by physical vapour deposition processes onto an oxide layer on the metallic substrate.

[0006] The ceramic thermal barrier coatings deposited by the physical vapour deposition technique have benefits over the ceramic thermal barrier coatings deposited by plasma spraying. The main benefit is improved thermal shock resistance due to the columnar structure of the ceramic thermal barrier coating produced by the physical vapour deposition process. Other benefits are improved erosion resistance and improved aerothermal performance.

[0007] However, despite these advantages, the ceramic thermal barrier coating deposited by the physical vapour deposition technique exhibits a thermal conductivity which is greater than that of a ceramic thermal barrier coating, of the same or similar composition, deposited by the plasma spray process. For example the thermal conductivity of a zirconia-8wt% yttria ceramic thermal barrier coating deposited by the PVD process is 2.0 W/m/K and the thermal barrier conductivity for the same ceramic thermal barrier coating deposited by the plasma spray process is 0.8-1.0 W/m/K. If all other factors are the same for the two methods of deposition of the ceramic thermal barrier coating, the greater conductivity of the ceramic thermal barrier coating deposited by the

PVD process means that a greater thickness of ceramic is required to achieve the equivalent insulating effect when compared to the ceramic thermal barrier coating deposited by the plasma spray process. This is an undesirable property because this necessitates a greater weight of ceramic thermal barrier coating on the metallic components of the gas turbine engine, and this is particularly undesirable for rotating components, e.g. turbine blades, because the additional weight may limit the temperature of operation due to a corresponding reduction in creep life of the metallic turbine blade.

[0008] Our European patent EP0628090 discloses one method of reducing the thermal conductivity of a ceramic thermal barrier coating deposited by physical vapour deposition, in which layers are produced in the columnar grains by depositing alternately by pure physical vapour deposition and by plasma assisted physical vapour deposition. The layers in the columnar grains increase the resistance to heat transfer through the ceramic thermal barrier coating.

[0009] It is known from European patent EPO166097 to provide a ceramic thermal barrier coating of zirconia with a first metallic oxide, yttria, to stabilise the zirconia and a second metallic oxide, ceria, to reduce the thermal conductivity of the ceramic thermal barrier coating. The cerium ion has an ionic radius different to the ionic radius of the zirconium ion and hence reduces phonon thermal conductivity.

[0010] It is also known that the addition of a second metallic oxide to zirconia stabilised with a first metallic oxide, yttria, reduces the phonon thermal conductivity if the second metallic ion has a valency different to the zirconium ion because of the appearance of extra vacancies in the zirconia lattice.

[0011] It is known from GB1519370 to provide a ceramic thermal barrier coating of zirconia with a first metallic oxide, yttria, magnesia, calcium oxide, lanthana or ceria, to stabilise the zirconia and a second metallic oxide, nickel oxide, zinc oxide or cobalt oxide to tailor the thermal shock resistance of the ceramic thermal barrier coating.

[0012] The present invention seeks to provide a stabilised zirconia thermal barrier coating which has reduced thermal conductivity.

[0013] The present invention provides a metallic article comprising a bond coating on the metallic article and a ceramic thermal barrier coating on the bond coating, heat being transported through the ceramic thermal barrier coating by phonon thermal conductivity and photon thermal conductivity, the ceramic thermal barrier coating comprising zirconia, a first suitable metallic oxide to stabilise the zirconia and a second metallic oxide to reduce the thermal conductivity of the ceramic thermal barrier coating, the metallic ion of the second metallic oxide has an ionic radius different to the ionic radius of the zirconium ion to reduce phonon thermal conductivity of the ceramic thermal barrier coating, the second metallic oxide is a different metallic oxide to the first metallic oxide,

the second metallic oxide is erbia or neodymia and absorbs energy in the 0.3 micrometers to 5 micrometers waveband to reduce photon thermal conductivity of the ceramic thermal barrier coating or the second metallic oxide is dysprosia, erbia, europia, gadolinia, neodymia, praseodymia or ytterbia and the ceramic thermal barrier coating (18) comprises a third metallic oxide which absorbs energy in the 0.3 micrometers to 5 micrometers waveband to reduce photon thermal conductivity of the ceramic thermal barrier coating, the third metallic oxide is nickel oxide, cobalt oxide or chromium oxide, the third metallic oxide is a different metallic oxide to the first metallic oxide and to the second metallic oxide.

[0014] Preferably the ceramic thermal barrier coating comprises 4 to 20wt% of the first metallic oxide, 5 to 25wt% of the second metallic oxide and the balance is zirconia plus incidental impurities.

[0015] Preferably the ceramic thermal barrier coating comprises 2 to 25mol% of the second metallic oxide.

[0016] Preferably the ceramic thermal barrier coating comprises 2at% to 25at% of the metallic ion of the second metallic oxide.

[0017] The first metallic oxide may be yttria, calcia, ceria, magnesia, india, scandia or ytterbia.

[0018] The bond coating may comprise a metal oxide, preferably alumina, layer on the metallic article.

[0019] The bond coating may comprise an aluminide, a platinum aluminide, an MCrAlY alloy or other aluminium containing alloy coating on the metallic article and a metallic oxide, preferably alumina, layer on the bond coating.

[0020] The bond coating may comprise an aluminium containing alloy coating on the metallic article, a platinum enriched aluminium containing alloy layer on the aluminium containing alloy coating, a platinum aluminide coating on the platinum enriched aluminium containing alloy layer and an alumina layer on the platinum aluminide coating.

[0021] The bond coating may comprise a platinum enriched outer layer on the metallic article and metallic oxide layer on the platinum enriched outer layer on the metallic article.

[0022] The metallic article may comprise a nickel superalloy or a cobalt superalloy.

[0023] The present invention also provides a method of applying a thermal barrier coating to a metallic article, comprising the steps of:- forming a bond coating on the metallic article, applying a ceramic thermal barrier coating to the bond coating, heat being transported through the ceramic thermal barrier coating by phonon thermal conductivity and photon thermal conductivity, the ceramic thermal barrier coating comprising zirconia, a first metallic oxide to stabilise the zirconia and a second metallic oxide to reduce the thermal conductivity of the ceramic thermal barrier coating, the metallic ion of the second metallic oxide having an ionic radius different to the ionic radius of the zirconium ion to reduce phonon thermal conductivity of the ceramic thermal barrier coating,

the second metallic oxide is a different metallic oxide to the first metallic oxide, the second metallic oxide is erbia or neodymia and the second metallic oxide absorbs energy in the 0.3 micrometers to 5 micrometers waveband to reduce photon thermal conductivity of the ceramic thermal barrier coating or the second metallic oxide is dysprosia, erbia, europia, gadolinia, neodymia, praseodymia or ytterbia and the ceramic thermal barrier coating comprises a third metallic oxide which absorbs energy in the 0.3 micrometers to 5 micrometers waveband to reduce photon thermal conductivity of the ceramic thermal barrier coating, the third metallic oxide is nickel oxide, cobalt oxide or chromium oxide, the third metallic oxide is a different metallic oxide to the first metallic oxide and to the second metallic oxide.

[0024] The present invention will be more fully described by way of example with reference to the accompanying drawings, in which:-

Figure 1 is a cross-sectional diagrammatic view through a metallic article having a thermal barrier coating according to the present invention,

Figure 2 is a cross-sectional diagrammatic view through a metallic article having another thermal barrier coating according to the present invention,

Figure 3 is a cross-sectional diagrammatic view through a metallic article having a further thermal barrier coating according to the present invention,

Figure 4 is a cross-sectional diagrammatic view through a metallic article having a further thermal barrier coating according to the present invention, and

Figure 5 is a graph of thermal conductivity against atomic % of erbia or ytterbia.

[0025] Referring to figure 1, illustrating the present invention there is shown part of a superalloy article 10 provided with a multi-layer thermal barrier coating indicated generally by numeral 12. It is shown in the as manufactured condition. The thermal barrier coating 12 comprises a bond coating 14 on the superalloy substrate 10, an oxide layer 16 on the bond coating 14 and a ceramic thermal barrier coating 18 on the oxide layer 16. The bond coating 14 is generally an aluminium containing alloy for example a MCrAlY alloy, a nickel aluminide, a cobalt aluminide or a platinum aluminide. The oxide generally contains alumina together with other oxides.

[0026] Another embodiment of the present invention is illustrated in figure 2 which shows part of a superalloy article 20 provided with a multi-layer thermal barrier coating indicated generally by numeral 22. It is shown in the as manufactured condition. The thermal barrier coating comprises a bond coating on the superalloy substrate 20, an oxide layer 32 on the bond coating and a ceramic thermal barrier coating 34 on the oxide layer 32. The bond coating comprises an aluminium containing alloy coating 24 on the metallic substrate 20, a platinum enriched aluminium containing alloy layer 26 on

the aluminium containing alloy coating 24, a platinum aluminide coating 28 on the platinum enriched aluminium containing alloy layer 26 and a platinum enriched gamma phase layer 30 on the platinum aluminide coating 28. The oxide layer 32 is on the platinum enriched gamma phase layer 30. The oxide generally comprises very pure alumina.

[0027] A further embodiment of the present invention is illustrated in figure 3 which shows part of a superalloy article 40 provided with a multi-layer thermal barrier coating indicated generally by numeral 42. It is shown in the as manufactured condition. The thermal barrier coating comprises an oxide layer 44 on the superalloy article 40 and a ceramic thermal barrier coating 46 on the oxide layer 44.

[0028] Another embodiment of the present invention is illustrated in figure 4 which shows part of a superalloy article 50 provided with a multi-layer thermal barrier coating 52. It is shown in the as manufactured condition. The thermal barrier coating 52 comprises a bond coating 54 on the superalloy substrate 50, an oxide layer 56 on the bond coating 54 and a ceramic thermal barrier coating 58 on the oxide layer 56. The bond coating 54 comprises a platinum enriched outer layer on the superalloy substrate 50. The platinum enriched outer layer comprises a platinum enriched gamma prime phase in the platinum enriched gamma phase matrix. The platinum enriched gamma prime phase breaks down to the platinum enriched gamma phase to release aluminium to form alumina in the oxide layer 56.

[0029] A conventional ceramic thermal barrier coating comprises 4 to 20wt% of one of yttria, ytterbia, ceria, indium, scandia or magnesia and the remainder is zirconia plus incidental impurities. The yttria, ytterbia, ceria, indium, scandia or magnesia is added to the zirconia to stabilise the zirconia in the tetragonal crystal structure.

[0030] The ceramic thermal barrier coatings shown in figures 1, 2, 3 and 4 preferably comprises 4 to 20wt% of one of yttria, ytterbia, ceria, indium, scandia or magnesia, 4 to 25mol%, or 5 to 25wt%, of one of erbium or neodymium and the remainder is zirconia plus incidental impurities. This is equivalent to adding about 2 to 25 at% of the metallic ion of the erbium or neodymium. The erbium or neodymium is added to a conventional stabilised ceramic thermal barrier coatings in order to reduce the thermal conductivity of the ceramic thermal barrier coating.

[0031] Alternatively the ceramic thermal barrier coatings shown in figures 1, 2, 3 and 4 comprises 4 to 20wt% of one of yttria, ytterbia, ceria, indium, scandia or magnesia, 4 to 25mol%, or 5 to 25wt%, of one of dysprosium, erbium, europium, gadolinium, neodymium, praseodymium or ytterbia, one of nickel oxide, cobalt oxide or chromium oxide and the remainder is zirconia plus incidental impurities. This is equivalent to adding about 2 to 25at% of the metallic ion of the dysprosium, erbium, europium, gadolinium, neodymium, praseodymium or ytterbia. The dysprosium, erbium, europium, gadolinium, neodymium, praseodymium or yt-

terbia and the nickel oxide, cobalt oxide or chromium oxide are added to a conventional stabilised ceramic thermal barrier coatings in order to reduce the thermal conductivity of the ceramic thermal barrier coating.

[0032] Referring to figure 5, which shows the theoretical thermal conductivity of yttria stabilised zirconia with varying amounts of replacement of zirconium with erbium or ytterbium in atomic%, it is seen that as the atomic% of erbium or ytterbium increases from 0 atomic% to 30 atomic% the theoretical thermal conductivity of the ceramic thermal barrier coating reduces from 1.4 W/mK to 1.1 W/mK. Thus a 2 at% replacement of zirconium with erbium would reduce thermal conductivity of the ceramic thermal barrier coating by 3.5%, a 4 at% replacement of zirconium with erbium would reduce thermal conductivity of the ceramic thermal barrier coating by 7%, a 8at% replacement of zirconium with erbium would reduce thermal conductivity of the ceramic thermal barrier coating by 10%, a 15 at% replacement of zirconium with erbium would reduce thermal conductivity of the ceramic thermal barrier coating by 18% and a 32 at% replacement of zirconium with erbium would reduce thermal conductivity of the ceramic thermal barrier coating by 21%.

[0033] In a series of experiments nickel superalloy articles were coated with a MCrAlY bond coating by plasma spraying or by electron beam physical vapour deposition, and a ceramic thermal barrier coating was deposited by electron beam physical vapour deposition onto the MCrAlY bond coats to produce an oxide inter-layer therebetween.

[0034] The compositions of the source of the ceramic thermal barrier coating was varied and the thickness of the thermal barrier coating was varied to see the effect of the variation of the composition of the ceramic thermal barrier coating. The composition of the source of the ceramic thermal barrier coating was varied by drilling a hole in a zirconia, 8wt% yttria source cylinder and by filling the hole with known amounts of erbium or ytterbium up to 25wt%, about 10mol%. The ceramic thermal barrier coatings were deposited at a rate of 3 micrometers per minute and thicknesses up to 550 micrometers were deposited.

EXAMPLE 1

[0035] A ceramic thermal barrier coating comprising 56.4wt% Zr, 19.1wt% O, 4.7wt% Y and 19.8wt% Er, equivalent to 31.2at% Zr, 60.2at% O, 2.7at% Y and 6.0at% Er, was deposited onto the MCrAlY bond coating. The ceramic thermal barrier coating comprises 71wt% zirconia, 6 wt% yttria and 23wt% erbium, which is equivalent to 87.8mol% zirconia, 3.8mol% yttria and 8.4mol% erbium. The ceramic thermal barrier coating was deposited to a thickness of 540 micrometers. The thermal conductivity of the ceramic thermal barrier coating was measured during a heating and a cooling cycle to 1200°C and had a thermal conductivity of 1.56 W/mK

during heating and 1.75 W/mK during cooling. The ceramic thermal barrier coating has a cubic structure.

EXAMPLE 2

[0036] A ceramic thermal barrier coating comprising 57.5wt% Zr, 18.4wt% O, 4.7wt% Y and 19.4wt% Er, equivalent to 32.3at% Zr, 59.0at% O, 2.7at% Y and 6.0at% Er, was deposited onto the MCrAlY bond coating. The ceramic thermal barrier coating comprises 72wt% zirconia, 6 wt% yttria and 22wt% erbia, which is equivalent to 88.1mol% zirconia, 3.7mol% yttria and 8.2mol% erbia. The ceramic thermal barrier coating was deposited to a thickness of 76 micrometers. The thermal conductivity of the ceramic thermal barrier coating was measured during a heating and a cooling cycle to 1200°C and had a thermal conductivity of 0.92 W/mK during heating and 0.98 W/mK during cooling. The ceramic thermal barrier coating has a cubic structure.

EXAMPLE 3 not in accordance with the invention

[0037] A ceramic thermal barrier coating comprising 61.2wt% Zr, 20.4wt% O, 4.8wt% Y and 13.7wt% Yb, equivalent to 32.3at% Zr, 61.3at% O, 2.6at% Y and 3.8at% Yb, was deposited onto the MCrAlY bond coating. The ceramic thermal barrier coating comprises 78wt% zirconia, 6 wt% yttria and 16wt% ytterbia, which is equivalent to 91.0mol% zirconia, 3.7mol% yttria and 5.4mol% ytterbia. The ceramic thermal barrier coating was deposited to a thickness of 134 micrometers. The thermal conductivity of the ceramic thermal barrier coating was measured during a heating and a cooling cycle to 1200°C and had a thermal conductivity of 1.44 W/mK during heating and 1.50 W/mK during cooling. The ceramic thermal barrier coating has a cubic structure.

EXAMPLE 4 not in accordance with the invention

[0038] A conventional ceramic thermal barrier coating comprising zirconia 8wt% yttria was deposited onto the MCrAlY bond coating. The ceramic thermal barrier coating was deposited to a thickness of 100 micrometers, 103 micrometers and 313 micrometers respectively for comparison with Examples 1 to 3. The thermal conductivity of the ceramic thermal barrier coatings was measured during a heating cycle to 1200°C and they had thermal conductivities of 1.31 W/mK, 1.01 W/mK and 1.63 W/mK respectively. The conventional ceramic thermal barrier coating has a tetragonal structure.

[0039] It can be seen from Examples 1 to 4 that the measured thermal conductivity changes with the thickness of the ceramic thermal barrier coating, irrespective of the composition of the ceramic thermal barrier coating.

[0040] We have found that in these examples for pure electron beam physical vapour deposited ceramic thermal

barrier coatings there is a change in the morphology from confused growth microstructure to columnar microstructure at thicknesses around 100 micrometers. For thicknesses of ceramic thermal barrier coating less than about 100 micrometers the addition of the second oxide to the ceramic thermal barrier coating does not significantly effect the thermal conductivity. However for ceramic thermal barrier coatings thicker than about 100 micrometers the addition of erbia or ytterbia clearly reduces the thermal conductivity. The measured thermal conductivity for the ceramic thermal barrier coating in Example 1 is 1.56 W/mK and this is 0.38 W/mK less than the predicted thermal conductivity of 1.94 W/mK for zirconia 8wt% yttria of 540 micrometers thickness. Such a difference represents a 20% reduction in thermal conductivity, by doping zirconia 8wt% yttria with 23wt% erbia or 8.4mol% erbia this is equivalent to 19.8wt% erbium or 6.0at% erbium.

[0041] The theory of thermal conductivity in crystalline solids is determined by the heat that is transferred by electrons, lattice vibrations and radiation. As zirconia and its alloys are electronic insulators, electrons play no part in the total thermal conductivity of a zirconia thermal barrier coating. The contribution to thermal conductivity from lattice vibrations may also be described as phonon conductivity as the quanta of lattice vibrations are known as phonons. The contribution to thermal conductivity from radiation may also be described as photon conductivity as the quanta of radiation are known as photons.

[0042] It is believed that the addition of the erbium or ytterbium, in the form of erbia or ytterbia, to the yttria stabilised zirconia distorts the zirconia lattice, introducing microstrain fields and providing a distribution of ions that have ionic radii greater than, ie different to, the ionic radius of the zirconium ion, and which act as scattering centres for phonons, and thus reduce phonon thermal conductivity. Other suitable metallic elements which form oxides and which have ions that have ionic radii greater than, different to, the ionic radius of the zirconium ion, may be used, for example dysprosium (Dy), europium (Eu), gadolinium (Gd), neodymium (Nd), and praseodymium (Pr) may be added to the yttria stabilised zirconia to reduce phonon thermal conductivity, these metallic elements are added in the form of oxides. Obviously other stabilising oxides may be used, and the appropriate second oxide addition may be used.

[0043] It is believed that the addition of erbia to the yttria stabilised zirconia also reduces the photon thermal conductivity. The erbia absorbs energy in the 0.3 to 5.0 microns waveband and this reduces the photon thermal conductivity because erbia is red. Other oxides which absorb energy in the 0.3 to 5.0 micrometers waveband may be used to reduce photon thermal conductivity, for example neodymia because neodymia is brown/yellow.

[0044] Erbia and neodymia are ideal additions to yttria stabilised zirconia to reduce the thermal conductivity of the ceramic thermal barrier coating because they reduce the phonon thermal conductivity because the er-

bium ion and neodymium ion have an ionic radius greater than, different to, the ionic radius of the zirconium ion, and they reduce the photon thermal conductivity because erbia and neodymia absorb energy in the 0.3 to 5.0 micrometers waveband.

[0045] A third oxide is added to the ceramic thermal barrier coating which comprises yttria, zirconia and a second oxide to reduce the thermal conductivity. The third oxide is selected to absorb energy in the 0.3 to 5.0 micrometers waveband, this reduces the photon thermal conductivity. At an operating temperature of 1500°C, the peak intensity occurs at 0.9 micrometers wavelength. The third oxide preferably has a dark colour, for example nickel oxide is green, cobalt oxide is blue/black and chromia is blue/black. Other third oxides which absorb energy in the 0.3 to 5.0 micrometers waveband may be used to reduce photon thermal conductivity.

[0046] The addition of the second oxide in the examples shown distributes the second oxide substantially evenly throughout the lattice structure of the ceramic thermal barrier coating.

[0047] The invention is applicable to zirconia stabilised with other suitable oxides, such as magnesia, calcia, scandia or india.

[0048] If ytterbia is used as the first oxide for stabilising the zirconia, then ytterbia is not used as the second oxide.

[0049] The invention is applicable to ceramic thermal barrier coatings applied by vapour deposition, for example chemical vapour deposition and physical vapour deposition, and to ceramic thermal barrier coatings applied by plasma spraying. The preferred method of depositing the ceramic thermal barrier coating is electron beam physical vapour deposition. The ceramic thermal barrier coating may be deposited by combustion chemical vapour deposition.

[0050] If the ceramic thermal barrier coating is applied by physical vapour deposition, it may additionally be applied by alternate deposition of layers by plasma assisted physical vapour deposition and by physical vapour deposition to modulate the structure of columnar grains to produce layers with different structure to reduce the thermal conductivity of the ceramic thermal barrier coating. It may be possible to produce these layers by changes in the amount of plasma assistance, or bias, rather than by switching between no plasma assistance and plasma assistance.

[0051] Any suitable amount of the second oxide may be used, for example it may be possible to use more than 25wt% and less than 5wt% and still obtain a reduction in thermal conductivity of the ceramic thermal barrier coating. However it is preferred to use sufficient second oxide so that more than 2at% and less than 30at% of the zirconium ions are replaced by the metallic ion of the second metallic oxide, because for additions above about 30at% of the metallic ion of the second metallic oxide the rate of decrease in thermal conductivity pro-

gressively decreases. Preferably more than 4at% and less than 25 at% of the zirconium ions are replaced by the metallic ion of the second metallic oxide, more preferably more than 8at% and less than 20 at% of the zirconium ions are replaced by the metallic ion of the second metallic oxide. Note that 2at% of the metallic ion of the second metallic oxide is equivalent to about 6-7wt% of the second metallic oxide, 4at% of the metallic ion of the second metallic oxide is equivalent to about 16-17wt% of the second metallic oxide, 8at% of the metallic ion of the second metallic oxide is equivalent to about 32wt% of the second metallic oxide, 20 at% of the metallic ion of the second metallic oxide is equivalent to about 64wt% of the second metallic oxide.

[0052] It is preferred to select second metallic oxides, or third metallic oxides, which prevent or do not aid the sintering of the ceramic thermal barrier coating. Thus it is preferred that the second metallic oxide, or third metallic oxide, prevents sintering of the ceramic thermal barrier coating because the sintering of the ceramic thermal barrier coating causes all the small voids, or pores, in the ceramic thermal barrier coating to be consolidated together to form a few larger voids or pores. It is believed that erbia, gadolinia, neodymia and ytterbia do not aid sintering or prevent sintering.

[0053] It is to be noted that the second metallic ion of the second metallic oxide has an ionic radius different to the zirconium ion. Preferably the second metallic ion has an ionic radius greater than the ionic radius of the zirconium ion. The difference in ionic radius between the zirconium ion and the second metallic ion distorts the zirconia lattice structure and hence reduces phonon thermal conductivity. It is also preferred that the atomic mass of the second metallic ion is larger than that of the zirconium ion so that the second metallic ions act as scattering centres for phonons to reduce the phonon thermal conductivity.

[0054] The use of the second metallic oxide or third metallic oxide which absorbs energy in the 0.3 micrometers to 5 micrometers waveband reduces the photon thermal conductivity, this is of major importance for metallic articles which operate at high temperatures such as gas turbine engine turbine blades, turbine vanes and combustion chambers.

[0055] The addition of the second oxide, which reduces phonon and photon thermal conductivity, enables the thickness of the ceramic thermal barrier coating to be reduced while achieving the same degree of thermal insulation. The addition of the second oxide, which reduces phonon thermal conductivity, and the third oxide, which reduces photon thermal conductivity, enables the thickness of the ceramic thermal barrier coating to be reduced while achieving the same degree of thermal insulation. Alternatively the same thickness of ceramic thermal barrier coating may be retained to achieve a greater degree of thermal insulation.

Claims

1. A metallic article (10) comprising a bond coating (14,16) on the metallic article (10) and a ceramic thermal barrier coating (18) on the bond coating (14,16), heat being transported through the ceramic thermal barrier coating by phonon thermal conductivity and photon thermal conductivity, the ceramic thermal barrier coating (18) comprising zirconia, a first suitable metallic oxide to stabilise the zirconia and a second metallic oxide to reduce the thermal conductivity of the ceramic thermal barrier coating (18), the metallic ion of the second metallic oxide having an ionic radius different to the ionic radius of the zirconium ion to reduce phonon thermal conductivity of the ceramic thermal barrier coating (18), the second metallic oxide is a different metallic oxide to the first metallic oxide, **characterised in that** the second metallic oxide is erbia or neodymia and the second metallic oxide absorbs energy in the 0.3 micrometers to 5 micrometers waveband to reduce photon thermal conductivity of the ceramic thermal barrier coating (18) or the second metallic oxide is dysprosia, erbia, europia, gadolinia, neodymia, praseodymia or ytterbia and the ceramic thermal barrier coating (18) comprises a third metallic oxide which absorbs energy in the 0.3 micrometers to 5 micrometers waveband to reduce photon thermal conductivity of the ceramic thermal barrier coating (18), the third metallic oxide is nickel oxide, cobalt oxide or chromium oxide, the third metallic oxide is a different metallic oxide to the first metallic oxide and to the second metallic oxide.
2. A metallic article as claimed in claim 1 wherein the ceramic thermal barrier coating (18) comprises 4 to 20wt% of the first metallic oxide, 5 to 25wt% of the second metallic oxide and the balance is zirconia plus incidental impurities.
3. A metallic article as claimed in claim 1 wherein the ceramic thermal barrier coating (18) comprises 2 to 25mol% of the second metallic oxide.
4. A metallic article as claimed in claim 1 wherein the ceramic thermal barrier coating (18) comprises 2at% to 25at% of the metallic ion of the second metallic oxide.
5. A metallic article as claimed in any of claim 1 to 4 wherein the first metallic oxide is yttria, calcia, ceria, magnesia, india, scandia or ytterbia.
6. A metallic article as claimed in any of claims 1 to 5 wherein the bond coating comprises a metal oxide layer (44) on the metallic article (40).
7. A metallic article as claimed in any of claims 1 to 6 wherein the bond coating comprises an aluminide, a platinum, aluminide, an MCrAlY alloy or other aluminium containing alloy coating (14) on the metallic article (10) and a metallic oxide layer (16) on the bond coating (14).
8. A metallic article as claimed in any of claims 1 to 6 wherein the bond coating comprises an aluminium containing alloy coating (24) on the metallic article (20), a platinum enriched aluminium containing alloy layer (26) on the aluminium containing alloy coating (24), a platinum aluminide coating (28) on the platinum enriched aluminium containing alloy layer (26) and an alumina layer (32) on the platinum aluminide coating (28).
9. A metallic article as claimed in any of claims 1 to 6 wherein the bond coating comprises a platinum enriched outer layer (54) on the metallic article (50) and a metallic oxide layer (56) on the platinum enriched outer layer (54) of the metallic article (50).
10. A metallic article as claimed in any of claims 1 to 9 wherein the metallic article (10) comprises a nickel superalloy or a cobalt superalloy.
11. A metallic article as claimed in any of claims 1 to 10 wherein the ceramic thermal barrier coating (18) has columnar grains.
12. A metallic article as claimed in claim 11 wherein the columnar grains have alternate layers with different structure to reduce thermal conductivity.
13. A metallic article as claimed in any of claims 1 to 12 wherein the ceramic thermal barrier coating is at least 100 microns thick.
14. A method of applying a thermal barrier coating to a metallic article (10), comprising the steps of: forming a bond coating (14,16) on the metallic article (10), applying a ceramic thermal barrier coating (18) to the bond coating (14,16), heat being transported through the ceramic thermal barrier coating by phonon thermal conductivity and photon thermal conductivity, the ceramic thermal barrier coating (18) comprising zirconia, a first metallic oxide to stabilise the zirconia and a second metallic oxide to reduce the thermal conductivity of the ceramic thermal barrier coating (18), the metallic ion of the second metallic oxide having an ionic radius different to the ionic radius of the zirconium ion to reduce phonon thermal conductivity of the ceramic thermal barrier coating (18), the second metallic oxide is a different metallic oxide to the first metallic oxide, **characterised in that** the second metallic oxide is erbia or neodymia and the second metallic oxide absorbs energy in the 0.3 micrometers to 5 micrometers wave-

- band to reduce photon thermal conductivity of the ceramic thermal barrier coating (18) or the second metallic oxide is dysprosia, erbia, europia, gadolinia, neodymia, praseodymia or ytterbia and the ceramic thermal barrier coating (18) comprises a third metallic oxide which absorbs energy in the 0.3 micrometers to 5 micrometers waveband to reduce photon thermal conductivity of the ceramic thermal barrier coating (18), the third metallic oxide is nickel oxide, cobalt oxide or chromium oxide, the third metallic oxide is a different metallic oxide to the first metallic oxide and to the second metallic oxide.
15. A method as claimed in claim 14 comprising applying a ceramic thermal barrier coating (18) comprises 4 to 20wt% of the first metallic oxide, 5 to 25wt% of the second metallic oxide and the balance is zirconia plus incidental impurities.
16. A method as claimed in claim 14 comprising applying a ceramic thermal barrier coating (18) comprises 2 to 25mol% of the second metallic oxide.
17. A metallic article as claimed in claim 14 wherein the ceramic thermal barrier coating (18) comprises 2at% to 25at% of the metallic ion of the second metallic oxide.
18. A method as claimed in any of claims 14 to 17 wherein the first metallic oxide is yttria, calcia, ceria, magnesia, india, scandia or ytterbia.
19. A method as claimed in any of claims 14 to 18 comprising oxidising the metallic article (40) to form a bond coating comprising a metal oxide layer (4\$) on the metallic article (44).
20. A method as claimed in any of claims 14 to 18 comprising applying an aluminide, a platinum aluminide, an MCrAlY alloy or other aluminium containing alloy bond coating (14) to the metallic article (10) and forming a metallic oxide layer (16) on the bond coating (14).
21. A method as claimed in any of claims 14 to 18 comprising applying an aluminium containing alloy coating (24) on the metallic article (20), forming a platinum enriched aluminium containing alloy layer (26) on the aluminium containing alloy coating (24), forming a platinum aluminide coating (28) on the platinum enriched aluminium containing alloy layer (26) and forming an alumina layer (32) on the platinum aluminide coating (28).
22. A method as claimed in any of claims 14 to 18 comprising forming a platinum enriched outer layer (54) on the metallic article (50) and forming a metallic oxide layer (56) on the platinum enriched outer layer (54) of the metallic article (50).
23. A method as claimed in any of claims 14 to 18 wherein the metallic article (10) comprises a nickel superalloy or a cobalt superalloy.
24. A method as claimed in any of claims 14 to 23 comprising applying the ceramic thermal barrier coating (18) by vapour deposition to produce columnar grains in the ceramic thermal barrier coating (18).
25. A method as claimed in claim 24 comprising applying the ceramic thermal barrier coating (18) by physical vapour deposition.
26. A method as claimed in claim 24 or claim 25 comprising applying the ceramic thermal barrier coating (18) by alternate plasma assisted vapour deposition and vapour deposition.
27. A method as claimed in any of claims 14 to 26 comprising applying the ceramic thermal barrier coating (18) to a thickness of a least 100 micrometers.

Patentansprüche

1. Metallischer Gegenstand (10) mit einem Verbundüberzug (14, 16) auf dem metallischen Gegenstand (10) und mit einem keramischen Wärmeschutzüberzug (18) auf dem Verbundüberzug (14, 16), bei welchem die Hitze durch den keramischen Wärmeschutzüberzug durch thermische Phononen-Leitfähigkeit und thermische Photonen-Leitfähigkeit übertragen wird und der keramische Wärmeschutzüberzug (18) folgende Bestandteile aufweist: Zirkoniumoxid, ein erstes geeignetes metallisches Oxid zur Stabilisierung des Zirkoniumoxids und ein zweites metallisches Oxid zur Verminderung der thermischen Leitfähigkeit des keramischen Wärmeschutzüberzugs (18), wobei das metallische Ion des zweiten metallischen Oxids einen Ionenradius aufweist, der unterschiedlich ist gegenüber dem Ionenradius des Zirkonium-Ions, um die thermische Phononen-Leitfähigkeit des keramischen Wärmeschutzüberzugs (18) zu vermindern und wobei das zweite metallische Oxid ein gegenüber dem ersten metallischen Oxid unterschiedliches metallisches Oxid ist, dadurch gekennzeichnet, daß das zweite metallische Oxid Erbiumoxid oder Neodymoxid ist und das zweite metallische Oxid Energie in einem Wellenband zwischen 0,3 Mikrometern und 5 Mikrometern absorbiert, um die thermische Photonen-Leitfähigkeit des keramischen Wärmeschutzüberzugs (18) zu vermindern oder dadurch gekennzeichnet, daß das zweite metallische Oxid Dysprosiumoxid, Erbiumoxid, Europiumoxid, Gadoliniumoxid,

- Neodymoxid, Praseodymoxid oder Ytterbiumoxid ist und der keramische Wärmeschutzüberzug (18) ein drittes metallisches Oxid aufweist, das Energie in einem Wellenband zwischen 0,3 Mikrometern und 5 Mikrometern absorbiert, um die thermische Photonen-Leitfähigkeit des keramischen Wärmeschutzüberzugs (18) zu vermindern, wobei das dritte metallische Oxid Nickeloxid, Kobaltoxid oder Chromoxid ist und das dritte metallische Oxid ein gegenüber dem ersten metallischen Oxid und gegenüber dem zweiten metallischen Oxid unterschiedliches metallisches Oxid ist.
2. Metallischer Gegenstand nach Anspruch 1, bei welchem der keramische Wärmeschutzüberzug (18) 4 bis 20 Gew. % des ersten metallischen Oxids, 5 bis 25 Gew. % des zweiten metallischen Oxids und als Rest Zirkoniumoxid plus zufällige Verunreinigungen enthält.
 3. Metallischer Gegenstand nach Anspruch 1, bei welchem der keramische Wärmeschutzüberzug (18) 2 bis 25 mol % des zweiten metallischen Oxids enthält.
 4. Metallischer Gegenstand nach Anspruch 1, bei welchem der keramische Wärmeschutzüberzug (18) 2 at % bis 25 at % der metallischen Ionen des zweiten metallischen Oxids enthält.
 5. Metallischer Gegenstand nach einem der Ansprüche 1 bis 4, bei welchem das erste metallische Oxid Yttriumoxid, Calciumoxid, Ceroxid, Magnesiumoxid, Indiumoxid, Scandiumoxid oder Ytterbiumoxid ist.
 6. Metallischer Gegenstand nach einem der Ansprüche 1 bis 5, bei welchem der Verbundüberzug eine Metalloxidschicht (44) auf dem metallischen Gegenstand (40) aufweist.
 7. Metallischer Gegenstand nach einem der Ansprüche 1 bis 6, bei welchem der Verbundüberzug ein Aluminid, ein Platin-Aluminid, eine MCrAlY-Legierung oder einen anderen Aluminium enthaltenden Legierungsüberzug (14) auf dem metallischen Gegenstand (10) und eine metallische Oxidschicht (16) auf dem Verbundüberzug (14) aufweist.
 8. Metallischer Gegenstand nach einem der Ansprüche 1 bis 6, bei welchem der Verbundüberzug einen Aluminium enthaltenden Legierungsüberzug (24) auf dem metallischen Gegenstand (20), eine mit Platin angereicherte Aluminium enthaltende Legierungsschicht (26) auf dem Aluminium enthaltenden Legierungsüberzug (24), einen Platin-Aluminid-Überzug (28) auf der mit Platin angereicherten Aluminium enthaltenden Legierungsschicht (26) und eine Aluminiumoxidschicht (32) auf dem Platin-Aluminid-Überzug (28) aufweist.
 9. Metallischer Gegenstand nach einem der Ansprüche 1 bis 6, bei welchem der Verbundüberzug eine mit Platin angereicherte äußere Schicht (54) auf dem metallischen Gegenstand (50) und eine metallische Oxidschicht (56) auf der mit Platin angereicherten äußeren Schicht (54) des metallischen Gegenstandes (50) aufweist.
 10. Metallischer Gegenstand nach einem der Ansprüche 1 bis 9, bei welchem der metallische Gegenstand (10) eine Nickel-Superlegierung oder eine Kobalt-Superlegierung ist.
 11. Metallischer Gegenstand nach einem der Ansprüche 1 bis 10, bei welchem der keramische Wärmeschutzüberzug (18) eine Stengelstruktur aufweist.
 12. Metallischer Gegenstand nach Anspruch 11, bei welchem die Stengelstruktur abwechselnde Schichten mit unterschiedlicher Struktur aufweist, um die thermische Leitfähigkeit zu vermindern.
 13. Metallischer Gegenstand nach einem der Ansprüche 1 bis 12, bei welchem der keramische Wärmeschutzüberzug wenigstens 100 Mikrometer dick ist.
 14. Verfahren zum Aufbringen eines Wärmeschutzüberzuges auf einem metallischen Gegenstand (10) mit den folgenden Schritten: es wird ein Verbundüberzug (14, 16) auf dem metallischen Gegenstand (10) gebildet; es wird ein keramischer Wärmeschutzüberzug (18) auf den Verbundüberzug (14, 16) aufgebracht; die Wärme wird durch den keramischen Wärmeschutzüberzug durch thermische Phononen-Leitfähigkeit und thermische Photonen-Leitfähigkeit übertragen; der keramische Wärmeschutzüberzug (18) weist Zirkoniumoxid, ein erstes metallisches Oxid zur Stabilisierung der Zirkoniumoxids und ein zweites metallisches Oxid auf, um die thermische Leitfähigkeit des keramischen Wärmeschutzüberzugs (18) zu vermindern; die metallischen Ionen des zweiten metallischen Oxids besitzen einen Ionenradius, der unterschiedlich ist von dem Ionenradius des Zirkonium-Ions, um die thermische Phononen-Leitfähigkeit des keramischen Wärmeschutzüberzugs (18) zu vermindern; das zweite metallische Oxid ist ein gegenüber dem ersten metallischen Oxid unterschiedliches Metalloxid, **dadurch gekennzeichnet, daß** das zweite metallische Oxid Erbiumoxid oder Neodymoxid ist und das zweite metallische Oxid Energie in einem Wellenband zwischen 0,3 Mikrometern und 5 Mikrometern absorbiert, um die thermische Photonen-Leitfähigkeit des keramischen Wärmeschutzüberzugs

- (18) zu vermindern oder **dadurch gekennzeichnet, daß** das zweite metallische Oxid Dysprosiumoxid, Erbiumoxid, Europiumoxid, Gadoliniumoxid, Neodymoxid, Praseodymoxid oder Ytterbiumoxid ist und daß der keramische Wärmeschutzüberzug (18) ein drittes metallisches Oxid aufweist, welches Energie in einem Wellenband zwischen 0,3 Mikrometern und 5 Mikrometern absorbiert, um die thermische Photonen-Leitfähigkeit des keramischen Wärmeschutzüberzugs (18) zu verringern, daß das dritte metallische Oxid Nickeloxid, Kobaltoxid oder Chromoxid ist und daß das dritte metallische Oxid ein gegenüber dem ersten metallischen Oxid und dem zweiten metallischen Oxid unterschiedliches metallisches Oxid ist.
15. Verfahren nach Anspruch 14, bei welchem der aufgebrachte keramische Wärmeschutzüberzug (18) 4 bis 20 Gew. % des ersten Oxids, 5 bis 25 Gew. % des zweiten metallischen Oxids und als Rest Zirkonoxid plus zufällige Verunreinigungen enthält.
16. Verfahren nach Anspruch 14, bei welchem der aufgebrachte keramische Wärmeschutzüberzug (18) 2 bis 25 mol % des zweiten metallischen Oxids aufweist.
17. Verfahren nach Anspruch 14, bei welchem der keramische Wärmeschutzüberzug (18) 2 at % bis 25 at % der metallischen Ionen des zweiten metallischen Oxids enthält.
18. Verfahren nach einem der Ansprüche 14 bis 17, bei welchem das erste metallische Oxid Yttriumoxid, Calciumoxid, Ceroxid, Magnesiumoxid, Indiumoxid, Scandiumoxid oder Ytterbiumoxid ist.
19. Verfahren nach einem der Ansprüche 14 bis 18, bei welchem der metallische Gegenstand (40) oxidiert wird, um einen Verbundüberzug, bestehend aus einer Metalloxidschicht (44), auf dem metallischen Gegenstand (40) zu schaffen.
20. Verfahren nach einem der Ansprüche 14 bis 18, bei welchem auf dem metallischen Gegenstand (10) ein Aluminid, ein Platin-Aluminid, eine $McrAlY$ -Legierung oder ein anderer Aluminium enthaltender Legierungs-Verbundüberzug (14) aufgebracht wird und eine metallische Oxidschicht (16) auf dem Verbundüberzug (14) gebildet wird.
21. Verfahren nach einem der Ansprüche 14 bis 18, bei welchem ein Aluminium enthaltender Legierungsüberzug (24) auf dem metallischen Gegenstand (20) aufgebracht wird und eine mit Platin angereicherte Aluminium-enthaltende Legierungsschicht (26) auf dem Aluminium enthaltenden Legierungsüberzug (24) aufgebracht wird und ein Platin-Aluminid-Überzug (28) auf der mit Platin angereicherten Aluminium enthaltenden Legierungsschicht (26) abgelagert wird und eine Aluminiumoxidschicht (32) auf den Platin-Aluminid-Überzug (28) aufgebracht wird.
22. Verfahren nach einem der Ansprüche 14 bis 18, bei welchem eine mit Platin angereicherte äußere Schicht (54) auf dem metallischen Gegenstand (50) aufgebracht und eine Metalloxidschicht (56) auf der mit Platin angereicherten äußeren Schicht (54) des metallischen Gegenstandes (50) erzeugt wird.
23. Verfahren nach einem der Ansprüche 14 bis 18, bei welchem der metallische Gegenstand (10) aus einer Nickel-Superlegierung oder einer Kobalt-Superlegierung besteht.
24. Verfahren nach einem der Ansprüche 14 bis 23, bei welchem der keramische Wärmeschutzüberzug (18) durch Dampfablagerung erzeugt wird, um eine Stengelstruktur in dem keramischen Wärmeschutzüberzug (18) zu erzeugen.
25. Verfahren nach Anspruch 24, bei welchem der keramische Wärmeschutzüberzug (18) durch physikalische Dampfablagerung erzeugt wird.
26. Verfahren nach Anspruch 24 oder 25, bei welchem der keramische Wärmeschutzüberzug (18) durch abwechselndes plasmaunterstütztes Dampfablagern und eine Dampfablagerung erfolgt.
27. Verfahren nach einem der Ansprüche 14 bis 26, bei welchem der keramische Wärmeschutzüberzug (18) bis zu einer Dicke von wenigstens 100 Mikrometern aufgetragen wird.

Revendications

1. Article métallique (10) comprenant un support d'encollage (14, 16) sur l'article métallique (10) et un revêtement céramique faisant barrière thermique (18) sur le support d'encollage (14, 16), la chaleur étant transportée à travers le revêtement céramique faisant barrière thermique par la conductivité thermique des phonons et la conductivité thermique des photons, le revêtement céramique faisant barrière thermique (18) comprenant le zircon, un premier oxyde métallique adéquat de manière à stabiliser le zircon et un deuxième oxyde métallique afin de réduire la conductivité thermique du revêtement céramique faisant barrière thermique (18), l'ion métallique du deuxième oxyde métallique ayant un rayon ionique différent du rayon ionique de l'ion zirconium afin de réduire la conductivité thermique des phonons du revêtement céramique faisant barrière

- thermique (18), le deuxième oxyde métallique est un oxyde métallique différent du premier oxyde métallique, **caractérisé en ce que** le deuxième oxyde métallique est l'oxyde d'erbium ou l'oxyde de néodyme et le deuxième oxyde métallique absorbe l'énergie dans la gamme d'ondes allant de 0,3 micromètres à 5 micromètres afin de réduire la conductivité thermique des photons du revêtement céramique faisant barrière thermique (18) ou le deuxième oxyde métallique est l'oxyde de dysprosium, l'oxyde d'erbium, l'oxyde d'euporium, l'oxyde de gadolinium, l'oxyde de néodyme, l'oxyde de praséodyme ou l'oxyde d'ytterbium et le revêtement céramique faisant barrière thermique (18) comprend un troisième oxyde métallique qui absorbe l'énergie dans la gamme d'ondes allant de 0,3 micromètres à 5 micromètres afin de réduire la conductivité thermique des photons du revêtement céramique faisant barrière thermique (18), le troisième oxyde métallique est l'oxyde de nickel, l'oxyde de cobalt ou l'oxyde de chrome, le troisième oxyde métallique est un oxyde métallique différent du premier oxyde métallique et du deuxième oxyde métallique.
2. Article métallique selon la revendication 1, dans lequel le revêtement céramique faisant barrière thermique (18) comprend de 4 à 20 % en poids du premier oxyde métallique, de 5 à 25 % en poids du deuxième oxyde métallique et l'équilibre est assuré par le zircon plus les impuretés incidentes.
 3. Article métallique selon la revendication 1, dans lequel le revêtement céramique faisant barrière thermique (18) comprend de 2 à 25 % mol du deuxième oxyde métallique.
 4. Article métallique selon la revendication 1, dans lequel le revêtement céramique faisant barrière thermique (18) comprend de 2 % atm à 25 % atm de l'ion métallique du deuxième oxyde métallique.
 5. Article métallique selon l'une quelconque des revendications 1 à 4, dans lequel le premier oxyde métallique est l'oxyde d'yttrium, l'oxyde de calcium, l'oxyde de cérium, l'oxyde de magnésium, l'oxyde d'indium, l'oxyde de scandium ou l'oxyde d'ytterbium.
 6. Article métallique selon l'une quelconque des revendications 1 à 5, dans lequel le support d'encollage comprend une couche d'un oxyde de métal (44) sur l'article métallique (40).
 7. Article métallique selon l'une quelconque des revendications 1 à 6, dans lequel le support d'encollage comprend un aluminide, un platine, un aluminide, un alliage MCrAlY ou un autre dépôt d'alliages contenant de l'aluminium (14) sur l'article métallique (10) et une couche d'un oxyde métallique (16) sur le support d'encollage (14).
 8. Article métallique selon l'une quelconque des revendications 1 à 6, dans lequel le support d'encollage comprend un dépôt d'alliages contenant de l'aluminium (24) sur l'article métallique (20), une couche d'alliages contenant de l'aluminium enrichi au platine (26) sur le dépôt d'alliages contenant de l'aluminium (24), un dépôt d'aluminide de platine (28) sur la couche d'alliages contenant de l'aluminium enrichi au platine (26) et une couche d'alumine (32) sur le dépôt d'aluminide de platine (28).
 9. Article métallique selon l'une quelconque des revendications 1 à 6, dans lequel le support d'encollage comprend une couche externe enrichie au platine (54) sur l'article métallique (50) et une couche d'un oxyde métallique (56) sur la couche externe enrichie au platine (54) de l'article métallique (50).
 10. Article métallique selon l'une quelconque des revendications 1 à 9, dans lequel l'article métallique (10) comprend un superalliage de nickel ou un superalliage de cobalt.
 11. Article métallique selon l'une quelconque des revendications 1 à 10, dans lequel le revêtement céramique faisant barrière thermique (18) comprend des grains en forme de colonnes.
 12. Article métallique selon la revendication 11, dans lequel les grains en forme de colonnes présentent une alternance de couches ayant une structure différente afin de réduire la conductivité thermique.
 13. Article métallique selon l'une quelconque des revendications 1 à 12, dans lequel le revêtement céramique faisant barrière thermique a une épaisseur d'au moins 100 microns.
 14. Méthode d'application d'un revêtement faisant barrière thermique sur un article métallique (10), comprenant les étapes de : - formation d'un support d'encollage (14, 16) sur l'article métallique (10), - application d'un revêtement céramique faisant barrière thermique (18) sur le support d'encollage (14, 16), la chaleur étant transportée à travers le revêtement céramique faisant barrière thermique par la conductivité thermique des phonons et la conductivité thermique des photons, le revêtement céramique faisant barrière thermique (18) comprenant le zircon, un premier oxyde métallique adéquat de manière à stabiliser le zircon et un deuxième oxyde métallique afin de réduire la conductivité thermique du revêtement céramique faisant barrière thermique (18), l'ion métallique du deuxième oxyde mé-

- tallique ayant un rayon ionique différent du rayon ionique de l'ion zirconium afin de réduire la conductivité thermique des phonons du revêtement céramique faisant barrière thermique (18), le deuxième oxyde métallique est un oxyde métallique différent du premier oxyde métallique, **caractérisé en ce que** le deuxième oxyde métallique est l'oxyde d'erbium ou l'oxyde de néodyme et le deuxième oxyde métallique absorbe l'énergie dans la gamme d'ondes allant de 0,3 micromètres à 5 micromètres afin de réduire la conductivité thermique des photons du revêtement céramique faisant barrière thermique (18) ou le deuxième oxyde métallique est l'oxyde de dysprosium, l'oxyde d'erbium, l'oxyde d'euprôm, l'oxyde de gadolinium, l'oxyde de néodyme, l'oxyde de praséodyme ou l'oxyde d'ytterbium et le revêtement céramique faisant barrière thermique (18) comprend un troisième oxyde métallique qui absorbe l'énergie dans la gamme d'ondes allant de 0,3 micromètres à 5 micromètres afin de réduire la conductivité thermique des photons du revêtement céramique faisant barrière thermique (18), le troisième oxyde métallique est l'oxyde de nickel, l'oxyde de cobalt ou l'oxyde de chrome, le troisième oxyde métallique est un oxyde métallique différent du premier oxyde métallique et du deuxième oxyde métallique.
15. Méthode selon la revendication 14 comprenant l'application d'un revêtement céramique faisant barrière thermique (18) qui comprend de 4 à 20 % en poids du premier oxyde métallique, de 5 à 25 % en poids du deuxième oxyde métallique et l'équilibre est assuré par le zircone plus les impuretés incidentes.
16. Méthode selon la revendication 14 comprenant l'application d'un revêtement céramique faisant barrière thermique (18) qui comprend de 2 à 25 % mol du deuxième oxyde métallique.
17. Article métallique selon la revendication 14, dans lequel le revêtement céramique faisant barrière thermique (18) comprend de 2 % atm à 25 % atm de l'ion métallique du deuxième oxyde métallique.
18. Méthode selon l'une quelconque des revendications 14 à 17, dans lequel le premier oxyde métallique est l'oxyde d'yttrium, l'oxyde de calcium, l'oxyde de cérium, l'oxyde de magnésium, l'oxyde d'indium, l'oxyde de scandium ou l'oxyde d'ytterbium.
19. Méthode selon l'une quelconque des revendications 14 à 18 comprenant l'oxydation de l'article métallique (40) de manière à former un support d'encollage comprenant une couche d'un oxyde de métal (44) sur l'article métallique (40).
20. Méthode selon l'une quelconque des revendications 14 à 18 comprenant l'application d'un aluminide, un aluminide de platine, un alliage MCrAlY ou d'un autre dépôt d'alliages contenant de l'aluminium (14) sur l'article métallique (10) et la formation d'une couche d'un oxyde métallique (16) sur le support d'encollage (14).
21. Méthode selon l'une quelconque des revendications 14 à 18 comprenant l'application d'un dépôt d'alliages contenant de l'aluminium (24) sur l'article métallique (20), la formation d'une couche d'alliages contenant de l'aluminium enrichi au platine (26) sur le dépôt d'alliages contenant de l'aluminium (24), la formation d'un dépôt d'aluminide de platine (28) sur la couche d'alliages contenant de l'aluminium enrichi au platine (26) et la formation d'une couche d'alumine (32) sur le dépôt d'aluminide de platine (28).
22. Méthode selon l'une quelconque des revendications 14 à 18 comprenant la formation d'une couche externe enrichie au platine (54) sur l'article métallique (50) et la formation d'une couche d'un oxyde métallique (56) sur la couche externe enrichie au platine (54) de l'article métallique (50).
23. Méthode selon l'une quelconque des revendications 14 à 18, dans lequel l'article métallique (10) comprend un superalliage de nickel ou un superalliage de cobalt.
24. Méthode selon l'une quelconque des revendications 14 à 23 comprenant l'application du revêtement céramique faisant barrière thermique (18) par déposition sous vide de manière à produire des grains en forme de colonnes dans le revêtement céramique faisant barrière thermique (18).
25. Méthode selon la revendication 24 comprenant l'application du revêtement céramique faisant barrière thermique (18) par dépôt physique en phase gazeuse.
26. Méthode selon la revendication 24 ou la revendication 25 comprenant l'application du revêtement céramique faisant barrière thermique (18) en alternant le dépôt physique en phase gazeuse assisté de la projection au plasma et le dépôt physique en phase gazeuse seul.
27. Méthode selon l'une quelconque des revendications 14 à 26 comprenant l'application du revêtement céramique faisant barrière thermique (18) sur une épaisseur d'au moins 100 micromètres.

Fig.1.




Fig.2.




Fig.3.




Fig.4.




Fig.5.

